

NOVALLOY E

MABS0E1

持续抗静电 ABS 树脂
Long-lasting Antistatic ABS resin

大赛璐 基本物性

DAICEL TYPICAL PROPERTIES

性能 Property	单位 Unit	试验法 ISO	测定条件 Test Condition	MABS0E1
物理性能 Mechanical				
拉伸强度 Tensile Strength	MPa	ISO 527		45
拉伸延伸率 Elongation	%	ISO 527		-
弯曲强度 Flexural Strength	MPa	ISO 178		60
弯曲弹性模量 Flexural Modulus	MPa	ISO 178		1900
Charpy 冲击强度 Charpy Impact Strength	KJ/m ²	ISO 179/1eA	4mm 宽, 23 °C 缺口	11
洛氏硬度 Rockwell Hardness	R	ISO 2039	R 级	-
热性能 Thermal				
热变形温度 Heat Deflection Temp	°C	ISO 75	4mm 宽, 1.80MPa 无退火, unannealed	72
热变形温度 Heat Deflection Temp	°C	ISO 75	4mm 宽, 0.45MPa 无退火, unannealed	85
其它性能 Miscellaneous				
比重 Specific Gravity	g/cm ³	ISO 1183		1.11
熔融指数 Melt Flow Rate	g/10min	ISO 1133	230°C/5kg	20
阻燃性能 Flame Resistance	(mm)	UL94	相当于 HB	1.57
表面电阻 Surface Resistance	Ω			10 ¹⁰⁻¹¹

- 注: 1. 此数值是实验代表性的数值, 但不是质量保证书的数值, 仅供参考;
These figures are merely typical characteristic figures of the trial ;
They are not quality guarantee figures and are for reference only;
2. 此数值可能会受着色剂种类和数量的影响;
These figures may be affected by type and quantity of the pigment;
3. 测试条件为 23 °C, 50%RH. Test condition is 23 °C, 50%RH.

Shanghai Daicel Polymers, Ltd.

地址: 上海市松江区泗泾镇望东中路 88 号
No.88Wangdong Middle Rd., Sijing Town
Songjiang Dist, Shanghai 201601

邮编: 201601

电话(Tel): 021-57619381

传真(Fax): 021-57619078

标准成型条件/Typical settings for processing

预干燥 Preliminary drying	料筒温度设定 (°C) Barrel temperature(deg C)				螺杆回转数 Screw rotation (rpm)	背压 Back pressure (MPa)	模具温度 Mold temperature (deg C)
	喷嘴 Nozzle	前部 Front	中部 Middle	后部 Back			
4-5 小时(hrs) 80-90°C	200-240	200-240	190-230	180-220	60-90	10-20	40-70